

CORROLESS CCI 250

CORROSION INHIBITOR

DESCRIPTION

A concentrated, clear, water borne, vapour phase corrosion inhibitor (VCI), developed for indoor use on steel.

PRODUCT FEATURES AND RECOMMENDED USES

- Accepted onto the **List of Approved Products suitable for use by the North Sea Oil and Gas industry**, based on testing for its environmental impact.
- **OCNS Registration Number 1412**
- Subject to normal government restrictions, CCI250 can be discharged into the marine environment.
- Used extensively as a hydro-test additive.
- Works by both contact and vapour phase inhibition and therefore protects above and below the water line when used in hydrotesting.
- Forms a clear film for easy inspection.
- Active period up to 2 years depending on use.
- Can be applied to equipment either in service, or in shutdown or preservation.
- Applications include steel coils and stacks, steel components, pumps and valve internals, enclosed cooling water systems, radiators etc.

TECHNICAL DATA

Volume Solids (±2%)	30%.
Specific gravity	1.02 kg/litre.
Film Thickness (nominal)	Wet Film 67 microns. Dry Film 20 microns.
Application	Brush, spray, dipping, flooding or fogging.
Mixing Ratio	Single Pack.
Theoretical Coverage	15 m ² /litre (nominal). Practical coverage rate can vary depending on application method, temperature, profile and porosity of the substrate.
Drying Time (at 18°C) at recommended dft	Dries to an oily finish in 48 hours.
Thinners and Cleaning solvent	Fresh water. (A detergent wash may be used for cleaning only).
Finish	Soft, oily, translucent finish.
Colours	Amber liquid.
Storage	Store in dry, cool conditions and protect from frost. Do not store below 2°C.

CORROLESS Corrosion Control, Worldwide Headquarters, Kelvin Way, WEST BROMWICH, West Midlands B70 7JZ,

Telephone:
+44 (0)121 524 2235

Fax:
+44 (0)121 553 2787

Web:
www.corroless.com

e-mail:
info-corroless@axaltacs.com

CORROLESS CCI 250

CORROSION INHIBITOR

APPLICATION DETAILS

Surface Preparation	For best results remove any oxides, dirt and grease etc. prior to application.
Application	<p>Stir thoroughly before use.</p> <p>For hydrotest applications, CCI 250 should be added to water systems at a minimum ratio of 1 part of CCI 250 to 100 parts of clean fresh water (by volume). A ratio of 2 to 5 parts CCI 250 to 100 parts of water are recommended for best results.</p> <p>CCI 250 may be introduced into a system by adding to the water, by spraying unthinned material directly onto components, by fogging unthinned material into void spaces (such as boilers) with compressed air or by any combination of the above. In order to extend the active period of the vapour phase protection, all normal vents, breather pipes and other openings should be sealed.</p> <p>In non-enclosed water systems, periodic recharging with CCI 250 is required to maintain a working concentration.</p>
Application Temperature	Range 2°C - 35°C.
Ambient Conditions	<p>Do not use below 2°C.</p> <p>Only apply in conditions of good ventilation, which should be maintained during drying.</p>
Flash Point	21 - 32°C.
Volatile Organic Content	388 g/litre
Health and Safety	At all times observe precautionary notices on containers. Refer to Material Safety Data Sheet available from Corroless on request.

AN AXALTA COATING SYSTEMS BRAND



The information provided herein corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since Axalta cannot anticipate all variations in actual end-use conditions Axalta makes no warranties and assumes no liability in connection with any of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights.