

## CORROLESS RF16 & RF16 (L)

### HIGH BUILD REINFORCED GLOSS TOPCOAT

#### DESCRIPTION

A single pack general purpose, glass reinforced, high build alkyd topcoat. Certain shades may contain lead colourants and these are labelled RF16 (L).

#### PRODUCT FEATURES AND RECOMMENDED USES

- Contains glass flake for improved impermeability and abrasion resistance.
- High build – reduces application costs and saves time.
- Good application properties.
- Fast drying compared to other high build alkyds, to help reduce the possibility of dust contamination shortly after application.
- Applications include pipes, mechanical equipment, bridges, fire escapes,

#### TECHNICAL DATA

**Volume Solids (±2%)**

42%.

**Volatile Organic Content**

500 g/litre (average)

**Specific Gravity**

0.9 to 1.10 kg/litre depending on colour.

**Film Thickness**

**Wet Film** 119 to 179 microns. **Dry Film** 50 to 75 microns.

**Theoretical Coverage**

8.4 m<sup>2</sup>/litre at 50 microns dft. Practical coverage rate can vary depending on application method, temperature, profile and porosity of the substrate.

**Mixing Ratio**

Single pack.

**Pot Life (at 18°C)**

Not applicable.

**Drying Times**  
at recommended dft

	10°C	18°C	30°C
<b>Dust Free</b>	2 hours	1½ hours	45 mins
<b>Hard Dry</b>	8 hours	6 hours	3 hours
<b>Overcoating Minimum</b>	24 hours	16 hours	10 hours
<b>Maximum</b>	Indefinite	Indefinite	Indefinite

**Thinners and Cleaning Solvent**

Corroless Thinners No.3 (spray) or No.2 (brush). (Solvent Gun Wash may be used for cleaning only).

**Finish**

Gloss.

**Colours**

Available in a wide range of colours.

**Storage**

Product has a shelf life of 2 years when stored in dry, cool conditions and protected from frost.

**CORROLESS Corrosion Control**, Worldwide Headquarters, Kelvin Way, WEST BROMWICH, West Midlands B70 7JZ,

**Telephone:**  
+44 (0)121 524 2235

**Fax:**  
+44 (0)121 553 2787

**Web:**  
[www.corroless.com](http://www.corroless.com)

**e-mail:**  
info-corroless@axaltacs.com

# CORROLESS RF16 & RF16 (L)

## HIGH BUILD REINFORCED GLOSS TOPCOAT

### APPLICATION DETAILS

**Surface Preparation** All surfaces when coated should be firm, clean, dry and free from all oil, grease, and other contamination.  
This is a finish coat and should be applied over Corroless primers.  
**Recommended primers:** Corroless S, SHB and QDR.

**Application:** Always follow the overcoating time for the selected primer.

Method	Airless Spray	Conventional Spray	Brush	Roller
Output Fluid Pressure	1800 - 2500psi	Yes – thinning required	Yes	Yes
Tip size	11-19 thou			
Fan angle	30-50°			

**Spray** For conventional spray an addition of up to 10% Corroless Thinners No.3 will be required.

**Brushing/Rolling** When brushing, apply unthinned, lay on, do not over brush. When rolling, an addition of up to 5% of Corroless Thinners No.2 may be needed. Brush application provides 50 to 60 microns dry.

**Mixing** Mix thoroughly before use.

**Stripe coating** Stripe coat all edges, nuts, bolts, welds etc.

**Application Temperature** Range 5°C - 30°C.

**Ambient Conditions** High humidity and condensation will impair gloss. Only apply in conditions of good ventilation, which should be maintained during drying. Do not apply when rain, mist, sleet or snow are imminent. During application and drying time the Relative Humidity should not exceed 85% and the steel temperature should remain at least 3°C above the dew point.

**Overcoating** Overcoatable with itself. If overcoating time exceeds 24 hours and contamination has occurred, clean using a detergent solution/fresh water rinse and allow to dry before continuing.

**Flash point** 21-32°C.

**Health and Safety** At all times observe precautionary notices on containers. Refer to Material Safety Data Sheets available from Corroless on request.

AN AXALTA COATING SYSTEMS BRAND



The information provided herein corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since Axalta cannot anticipate all variations in actual end-use conditions Axalta makes no warranties and assumes no liability in connection with any of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights.