

## **CORROLESS CCI 355**

### **CORROSION INHIBITOR (HEAVY DUTY GREASE)**

#### **DESCRIPTION**

A vapour phase corrosion inhibiting (VCI), extreme pressure, lithium grease which can be applied directly onto surfaces requiring continuous lubrication, in areas subject to heavy or shock loading.

#### **PRODUCT FEATURES AND RECOMMENDED USES**

- Protects by both contact and vapour action.
- Effective even when moisture, oil and rust are already present.
- Highly resistant to water and steam.
- Gives up to 3 years protection in aggressive environments.
- Contains molybdenum disulphide for improved load carrying properties.
- Will protect wire ropes, machinery and equipment both in operation and storage.
- Applications include chains, wire ropes, bearings, conveyors, spindles, open gearing, etc.

#### **TECHNICAL DATA**

<b>NLG1 Classification</b>	2.
<b>Worked Penetration (IP50)</b>	265/295.
<b>Operating Temperature</b>	-30°C to +130°C.
<b>Drop Point (IP132)</b>	180°C minimum.
<b>Specific Gravity</b>	0.97 kg/litre.
<b>Mixing Ratio</b>	Single pack.
<b>Drying time (at 18°C)</b>	Not applicable - does not dry.
<b>Thinners and Cleaning solvent</b>	Use unthinned. White spirit may be used for cleaning.
<b>Finish</b>	Matt.
<b>Colour</b>	Black.
<b>Storage</b>	Product has a shelf life of 2 years when stored in dry, cool conditions and protected from frost.

**CORROLESS Corrosion Control**, Worldwide Headquarters, Kelvin Way, WEST BROMWICH, West Midlands B70 7JZ,

**Telephone:**  
+44 (0)121 524 2235

**Fax:**  
+44 (0)121 553 2787

**Web:**  
[www.corroless.com](http://www.corroless.com)

**e-mail:**  
info-corroless@axaltacs.com

# CORROLESS CCI 355

## CORROSION INHIBITOR (HEAVY DUTY GREASE)

### APPLICATION DETAILS

<b>Recommended Substrates</b>	Steel and most other metallic substrates.
<b>Surface Preparation</b>	No special surface preparation is required, but the cleaner the substrate, the more effective will be the protection achieved from the product. For best results, remove any dirt, grease, moisture or condensation prior to application.
<b>Application</b>	CCI 355 is a concentrated corrosion inhibitor that can be applied to equipment either in service, shut down or in preservation situations. Apply by grease gun, brush or by hand using a 'hairy mitt'. Although CCI 355 does not normally require removal prior to recommissioning equipment, it can be removed using conventional solvents such as white spirit.
<b>Mixing</b>	Apply as supplied.
<b>Application Temperature</b>	2°C to 35°C.
<b>Ambient Conditions</b>	Apply in good weather conditions with Relative Humidity not exceeding 85% and steel temperature at least 3°C above the Dew Point
<b>Flash Point (IP34)</b>	250°C.
<b>Volatile Organic Content</b>	Not applicable
<b>Health and Safety</b>	At all times observe precautionary notices on containers. Refer to Material Safety Data Sheet available from Corroless on request.

AN AXALTA COATING SYSTEMS BRAND



The information provided herein corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since Axalta cannot anticipate all variations in actual end-use conditions Axalta makes no warranties and assumes no liability in connection with any of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights.