

CORROLESS CCI FUEL ADDITIVE

DESCRIPTION A blend of liquid and vapour phase corrosion inhibitors (VCI) in a light mineral oil, developed for protection of fuel tanks.

PRODUCT FEATURES AND RECOMMENDED USES

- Works by both contact and vapour phase inhibition.
- Can be used for both empty, partially full and full tanks.
- No adverse effect on the stored fuel

TECHNICAL DATA

Specific gravity	0.92 kg/litre.
Storage	Store in dry, cool conditions.
Flash Point	170°C.
Volatile Organic Content (g/litre)	Not applicable

CORROLESS CCI FUEL ADDITIVE

TREATMENT

The product can be used in several ways depending on the on the fill level in the tank.

EMPTY FUEL TANKS

Empty fuel tanks may be protected in two ways

1. The tank may be filled with fuel additive and then drained, The excess fuel additive may be retained for further use.
2. If flooding is not economically practical the additive may be misted into the tank at the rate of 250 gm per cubic metre (0.025%)

FULL OR PARTIALLY FULL TANKS

Because the fuel acts as a diluent and also degrades the walls of the tank the additive must be used at 12 gm per litre in the fuel plus 500 gm per cubic metre (0.05%) of void space left in the tank.

When misting it will help if the product is thinned with 5-10% of the fuel in the tank.

STORAGE Product has a shelf life of 2 years when stored in dry, cool conditions and protected from frost.

AN AXALTA COATING SYSTEMS BRAND



The information provided herein corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since Axalta cannot anticipate all variations in actual end-use conditions Axalta makes no warranties and assumes no liability in connection with any of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights.