

CORROLESS RF65

TWO PACK POLYURETHANE REINFORCED FINISH

DESCRIPTION

A two-component, glass reinforced, acrylic urethane, semi-gloss topcoat.

PRODUCT FEATURES AND RECOMMENDED USES

- Excellent colour and UV resistance.
- Indefinitely recoatable.
- Tough durable semi-gloss finish, good anti-abrasion resistance and weathering characteristics and chemical resistance. Approved for use by Network Rail (approved systems available on request).
- Glass reinforced for increased impermeability.
- Suitable for urban, marine or industrial environments.
- Applications include piping, cranes, mechanical equipment, bridges, storage tank exteriors, chemical plants and other structural steel.

TECHNICAL DATA

Volume Solids (±2%)

58%.

Volatile Organic Content

Base 431 g/litre (average) **Hardener** 112 g/litre

Specific Gravity

1.4 to 1.6 kg/litre (mixed material) depending on colour.

Film Thickness

Wet Film 52 - 86 microns. **Dry Film** 30 - 50 microns.

Theoretical Coverage

11.6 m²/litre at 50 microns dft. Practical coverage rate can vary depending on application method, temperature, profile and porosity of the substrate.

Mixing Ratio

9:1 by volume (base to hardener).

Pot Life (at 18°C)

4 hours.

Drying Times (at 50 microns dft)

	10°C	18°C	30°C
Dust Free	2 hours	1½ hours	45 minutes
Hard Dry	6 hours	4 hours	2 hours
Overcoating Minimum	24 hours	16 hours	12 hours
Maximum	Indefinite	Indefinite	Indefinite

Thinners and Cleaning solvent

Corroless Thinners No.5. (Solvent Gun Wash may be used for cleaning only).

Finish

Mid sheen.

Colours

Available in a wide range of colours.

Storage

Product has a shelf life of 2 years when stored in dry, cool conditions and protected from frost.

CORROLESS Corrosion Control, Worldwide Headquarters, Kelvin Way, WEST BROMWICH, West Midlands B70 7JZ,

Telephone:
+44 (0)121 524 2235

Fax:
+44 (0)121 553 2787

Web:
www.corroless.com

e-mail:
info-corroless@axaltacs.com

CORROLESS RF65

TWO PACK POLYURETHANE REINFORCED FINISH

APPLICATION DETAILS

Surface Preparation All surfaces when coated should be firm, clean, dry and free from all oil, grease, and other contamination. This is a finish coat and should be applied over Corroless primers or intermediate coats.
Recommended primers: Corroless EPF.
Intermediate coats: Corroless RF31.

Application Always follow the overcoating time for the selected primer.

Method	Airless Spray	Conventional Spray	Brush	Roller
Output Fluid Pressure	2200-2500 psi	Yes – thinning required	Yes	Yes
Tip size	13-18 thou			
Fan angle	30° - 65°			

Spraying **Caution** contains **isocyanate**. Ensure adequate ventilation and wear air fed hood when spraying. **Airless spray** - an addition of up to 5% Corroless Thinners No.5 may used for application at lower film builds or under cool conditions. **Conventional Spray** - an addition of up to 10% Corroless Thinners No.5 will be necessary for conventional spray. Maximum dry film thickness by this method is 75 microns.

Brushing/Rolling Suitable for brush or roller.

Mixing Mix each component separately prior to thoroughly mixing together for 2 to 3 minutes at medium speed. Always use a mechanical agitator. Ensure product is used only in the proportions recommended.

Stripe coating Stripe coat all edges, nuts, bolts, welds etc.

Application Temperature Range 5°C - 25°C.

Ambient Conditions Only apply in conditions of good ventilation, which should be maintained during drying. Do not apply when rain, mist, sleet or snow are imminent. During application and drying time the Relative Humidity should not exceed 85% and the steel temperature should remain at least 3°C above the dew point.

Overcoating Overcoatable with itself and Corroless Anti-graffiti topcoats. If overcoating time exceeds 24 hours and contamination has occurred, clean using a detergent solution/fresh water rinse and allow to dry before continuing.

Flash Point 21-32°C.

Health and Safety At all times observe precautionary notices on containers. Refer to Material Safety Data Sheets available from Corroless on request.

AN AXALTA COATING SYSTEMS BRAND



The information provided herein corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since Axalta cannot anticipate all variations in actual end-use conditions Axalta makes no warranties and assumes no liability in connection with any of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights.