

Corroless ACO Mastic Rapid Grade

(Formerly Acothane Mastic Rapid Grade)

Issue Date: Mar 2019
 Issue: 2
 Page 1 of 2

Product Description	A solvent free, fast curing, two pack polyurethane repair mastic for pipe coatings.			
Features & Use	<ul style="list-style-type: none"> Use for the coating of field joints, repair of damaged coatings, filling of holes and cracks, on steel pipelines and other steel structures This Rapid grade is specifically developed for use at lower ambient temperatures. For temperatures above 25°C the Mastic Standard Grade should be used, as this Rapid grade will be too fast curing 			
Approvals/ Certification	<ul style="list-style-type: none"> Meets the requirements of GBE/CW6 Part 1 for External Pipe Protection BS6920 Factory and site application and WRAS water fittings directory Meets the performance requirements of BS EN 10290 and AWWA C222 Malaysian SPAN approved Approvals held in the former name of 'Acothane' 			
Finish	Sheen			
Volume Solids	100%			
VOC Content	0 g/litre			
Film Thickness Range And Coverage		Dry Film Thickness	Wet Film Thickness	Theoretical Coverage
	Typical	1 mm	1 mm	1.0 m ² /litre
	Typical	5 mm	5 mm	0.2 m ² /litre
Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated				
Drying Times	Applied to 1.0 mm DFT	+10°C	+20°C	+30°C
	Dust Free	40 min	15 min	5 min
	Hard Dry	1½ hr	40 min	20 min
	Overcoating	40 min	15 min	5 min
	Full Cure	7 days	6 days	5 days
Drying and recoating times are related to the surface temperature				
Colours	Grey and a limited range of other shades			
Mix Ratio/ Product Code	10AMR (base) and 10ACT (activator) Base 3 parts by volume 3.23 parts by Weight Hardener 1 part by volume 1 part by Weight			
Pot Life	approx. 5 min at 25°C			
SG	1.29 kg/lit mixed			
Storage Conditions	Store in dry, cool conditions and protect from frost			
Shelf Life	Minimum 24 months if stored as above in unopened containers			
Flash Point	Above 60°C			

Corroless ACO Mastic Rapid Grade

Issue Date: Mar 2019
Page 2 of 2

<p>Surface Preparation</p>	<ul style="list-style-type: none"> All surfaces to be coated should be dry and cleaned as necessary to remove all oil, grease, salts, weld flux or other contamination. Where necessary, remove weld spatter and grind smooth all sharp edges and weld seams Steel: blast clean to minimum Sa2½ (ISO 8501-1:2007), surface profile depth 75-100µm. Mechanical tools may also be used providing a profile of minimum 75µm. <u>Do not polish the steel surface</u> Overlap onto existing pipeline coating: remove any loose material to establish a firm edge. Feather sound coating and abrade surface to provide a key. Thoroughly abrade to remove gloss, surface contaminants etc. by suitable method (sweep blasting, abrasive disk etc.) Concrete: remove all laitance and other contaminants by most appropriate methods. Ensure the concrete is dry to a reading of <16% on the Wood Moisture Equivalent (WME) scale. Prime with Corroless ACO LV Sealer 										
<p>Mixing</p>	<p>Mix only in the proportions stated, mixing each component individually then together using a mechanical agitator. Activator must be added to base and thoroughly mixed to ensure an even mix throughout the container – at least 2 minutes mixing time is recommended. Care must be taken to avoid unmixed material being left on sides and bottom of can. Decanting mixed material into a plastic container and further mixing is recommended. Plastic container may be recovered for further use when coating has cured.</p>										
<p>Thinner / Cleaner</p>	<p>Do not thin / Axalta Thinner Fast Industrial TH120 (formerly called No.4 Thinner)</p>										
<p>Application Conditions</p>	<p>Do not apply when rain, mist, sleet or snow are imminent. Normal application requires relative humidity below 80%. To avoid risk of condensation, application should be performed only when the steel surface temperature is at least 3°C (5°F) above the dew point. Application at temperatures below 1°C (33°F) must be carefully monitored, since the possible presence of ice on the surface (or in pores, in the case of concrete) will result in poor performance.</p>										
<p>Application Methods</p>	<table border="1" data-bbox="483 1081 1520 1176"> <thead> <tr> <th>Method</th> <th>Airless Spray</th> <th>Conventional Spray</th> <th>Brush</th> <th>Roller</th> </tr> </thead> <tbody> <tr> <td></td> <td>No</td> <td>No</td> <td>Yes</td> <td>No</td> </tr> </tbody> </table> <ul style="list-style-type: none"> Designed for application by brush, roller, putty knife, trowel or spatula 	Method	Airless Spray	Conventional Spray	Brush	Roller		No	No	Yes	No
Method	Airless Spray	Conventional Spray	Brush	Roller							
	No	No	Yes	No							
<p>Product Notes</p>	<ul style="list-style-type: none"> Activator contains isocyanates – refer to Safety Data Sheet Overcoating - abrading will be required if overcoating after 24 hours In-service temperature limits: Wet – 0°C to 70°C depending on solution; Dry – minus 20°C to + 120°C continuous In order to comply with WRAS certification, a minimum cure time of 14 days at 7°C is required before contact with drinking water Corroless ACO Mastic Rapid has excellent adhesion to abraded Fusion Bonded Epoxy (FBE), and suitably prepared 3LPE and 3LPP. Please consult Axalta Coating Systems for technical advice Can be used in operations requiring fast cure, e.g. lay barge, weld coating and encapsulation of anode connectors, coating repair prior to trenching/backfilling. Corroless ACO Standard Mastic should be used for less speed-critical coating operations and at temperatures above 25°C 										
<p>Health & Safety</p>	<p>Containers are provided with safety labels which should be observed. Further information about hazardous influences and protection are detailed in individual Product Safety Data Sheets. A Safety Data Sheet for this product is available on request from Axalta Coating Systems.</p>										

AN AXALTA COATING SYSTEMS BRAND



The information provided herein corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since Axalta cannot anticipate all variations in actual end-use conditions Axalta makes no warranties and assumes no liability in connection with any of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. This product is for professional use only.