

# Corroless ACO Spray Grade

(formerly Acothane Spray Grade)

<b>Product Description</b>	<b>A high build, solvent free, two pack polyurethane</b> coating for spray application onto steel pipes and field joints.				
<b>Features &amp; Use</b>	<ul style="list-style-type: none"> <li>Outstanding physical properties in terms of flexural strength, tensile strength, impact and abrasion resistance</li> <li>Use for the protection of steel and concrete structures in aggressive environments e.g. internal and external protection of pipelines, field joints, offshore splash zones, bridge protection, chemical plants</li> </ul>				
<b>Approvals/ Certification</b>	<ul style="list-style-type: none"> <li>Meets the requirements of GBE/CW6 Part 1 for External Pipe Protection</li> <li>BS6920 Factory and site application</li> <li>Meets the performance requirements of BS EN 10290 and AWWA C222</li> <li>Malaysian SPAN approved</li> <li>Approvals held in the former name of 'Acothane'</li> </ul>				
<b>Finish</b>	Sheen				
<b>Volume Solids</b>	100%				
<b>VOC Content</b>	0 g/litre				
<b>Film Thickness Range And Coverage</b>		<b>Dry Film Thickness</b>	<b>Wet Film Thickness</b>	<b>Theoretical Coverage</b>	
	<b>Typical</b>	0.5 mm	0.5 mm	2.0 m <sup>2</sup> /litre	
	<b>Typical</b>	5 mm	5 mm	0.2 m <sup>2</sup> /litre	
Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated					
<b>Drying Times</b>	Applied to 1 mm DFT	<b>+10°C</b>	<b>+20°C</b>	<b>+30°C</b>	<b>+40°C</b>
	<b>Dust Free</b>	50 min	30 min	15 min	10 min
	<b>Hard Dry</b>	8 hr	4 hr	3 hr	2 hr
	<b>Stackable</b>	16 hr	8 hr	7 hr	7 hr
	<b>Full Cure</b>	7 days	7 days	6 days	5 days
	Drying and recoating times are related to the surface temperature				
<b>Colours</b>	Cream, Grey and a limited range of other shades				
<b>Mix Ratio/ Product Code</b>	<b>10SGR</b> (base) and <b>10ACT</b> (activator) Base 3 parts by volume 3.23 parts by Weight Hardener 1 part by volume 1 part by Weight				
<b>Pot Life</b>	5 min at 20°C				
<b>SG</b>	1.29 kg/lit mixed				
<b>Storage Conditions</b>	Store in dry, cool conditions and protect from frost				
<b>Shelf Life</b>	Minimum 24 months if stored as above in unopened containers				
<b>Flash Point</b>	Above 60°C				

# Corroless ACO Spray Grade

Issue Date: Mar 2019  
Page 2 of 2

<p><b>Surface Preparation</b></p>	<ul style="list-style-type: none"> <li>All surfaces to be coated should be dry and cleaned as necessary to remove all oil, grease, salts, weld flux or other contamination. Where necessary, remove weld spatter and grind smooth all sharp edges and weld seams</li> <li><b>Steel:</b> blast clean to minimum Sa2½ (ISO 8501-1:2007), surface profile depth 75-100µm. Mechanical tools may also be used providing a profile of minimum 75µm. <u>Do not polish the steel surface</u></li> <li><b>Concrete:</b> remove all laitance and other contaminants by most appropriate methods. Ensure the concrete is dry to a reading of &lt;16% on the Wood Moisture Equivalent (WME) scale. Prime with Corroless ACO LV Sealer</li> </ul>				
<p><b>Mixing</b></p>	<p>Twin feed equipment required</p>				
<p><b>Thinner / Cleaner</b></p>	<p>Do not thin / Axalta Thinner Fast Industrial TH120 (formerly called No.4 Thinner)</p>				
<p><b>Application Conditions</b></p>	<p>Do not apply when rain, mist, sleet or snow are imminent. Normal application requires relative humidity below 80%. To avoid risk of condensation, application should be performed only when the steel surface temperature is at least 3°C (5°F) above the dew point. Application at temperatures below 1°C (33°F) must be carefully monitored, since the possible presence of ice on the surface (or in pores, in the case of concrete) will result in poor performance.</p>				
<p><b>Application Methods</b></p>	<p><b>Method</b></p>	<p><b>Airless Spray</b></p>	<p><b>Conventional Spray</b></p>	<p><b>Brush</b></p>	<p><b>Roller</b></p>
<p style="text-align: center;">See below</p>					
<ul style="list-style-type: none"> <li>Twin component hot airless spray required with instant purge capability due to very short pot life – please consult Axalta Coating Systems for advice</li> <li>Note that the use of the Sulzer cartridge spraying system or other low-pressure spraying systems is not permitted for Drinking water applications requiring WRAS approvals</li> </ul>					
<p><b>Product Notes</b></p>	<ul style="list-style-type: none"> <li><b>Activator contains isocyanates</b> – refer to Safety Data Sheet</li> <li>Overcoating - normally after 1 hour and within 24 hours of initial application. Abrading will be required if overcoating after 24 hours</li> <li>In-service temperature limits: Wet – 0°C to 70°C depending on solution; Dry – minus 20°C to + 120°C continuous</li> <li>A minimum cure time of 14 days at 7°C is required before contact with drinking water</li> <li>Curing rate will be retarded below 10°C</li> <li>Backfilling or immersion can normally be carried out as soon as the coating is Hard Dry</li> <li>Spark/Holiday testing: maximum 5KV after the coating is hard dry</li> <li>Corroless ACO Spray Grade has excellent adhesion to abraded Fusion Bonded Epoxy (FBE), and suitably prepared 3LPE and 3LPP. Please consult Axalta Coating Systems for technical advice</li> </ul>				
<p><b>Health &amp; Safety</b></p>	<p>Containers are provided with safety labels which should be observed. Further information about hazardous influences and protection are detailed in individual Product Safety Data Sheets. A Safety Data Sheet for this product is available on request from Axalta Coating Systems.</p>				

AN AXALTA COATING SYSTEMS BRAND



The information provided herein corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since Axalta cannot anticipate all variations in actual end-use conditions Axalta makes no warranties and assumes no liability in connection with any of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. This product is for professional use only.